


WEST COAST FILTERS INC.

Design, Manufacture & Distribution of Water Purification Equipment

Filter Sand .45 - .55 mm Product Sand



Typical Product Analysis:

USA Sieve	% Retained	% Cumulative	% Passing
16 Mesh	0.1	0.1	99.9
20 Mesh	9.2	9.3	90.7
30 Mesh	39.0	49.2	50.8
35 Mesh	29.4	78.6	21.4
40 Mesh	13.6	92.2	7.8
50 Mesh	6.1	98.3	1.7
100 Mesh	1.7	100.0	0
Pan	0.0	100.0	0
E.S.	0.47		
U.C.	1.42		

Technical Data:

Acid Solubility	<1%	% Fe ₂ O ₃	0.083
Specific Gravity	2.64	% Al ₂ O ₃	0.134
Porosity	40	% MgO	0.010
Moh Hardness	7.0	% Na ₂ O	0.008
% Fractured Faces	N/A	% Cr ₂ O ₃	0.000
Fusion Point	3,150°	% CaO	0.012
Roundness	0.8 ***	% K ₂ O	0.031
Sphericity	0.8 ***	% TiO ₂	0.021
Bulk Density	100# / ft. ³	% LOL	0.141
		% SiO ₂	99.555

*** As determined by an independent lab using the methods outlined in "Elements of Water Supply and Wastewater Disposal", 2nd edition, John Wiley & sons, Inc.