


WEST COAST FILTERS INC.

Design, Manufacture & Distribution of Water Purification Equipment

Filter Gravel 3/4" X 1/2"



Typical Product Analysis:

USE Sieve	% Retained	% Cumulative	% Passing
1"	0.0	0.0	100.0
3/4"	2.2	2.2	97.8
1/2"	94.5	96.7	3.3
3/8"	2.9	99.6	0.4
Pan	0.4	100.0	0.0

Technical Data:

Acid Solubility	< 1%	% Fe ₂ O ₃	0.083
Specific Gravity	2.64	% Al ₂ O ₃	0.134
Porosity	40	% MgO	0.010
Moh Hardness	7.0	% Na ₂ O	0.008
% Fractured Faces	< 25%	% Cr ₂ O ₃	0.000
Flat & Elongates	< 2%	%CaO	0.012
Fusion Point	3,150°	% K ₂ O	0.031
Roundness	0.8 ***	% TiO ₂	0.021
Sphericity	0.8 ***	% LOL	0.141
Bulk Density	100# / ft. ³	% SiO ₂	99.555

*** As determined by an independant lab using the methods outlined in "Elements of Water Supply and Wastewater Disposal", 2nd edition, John Wiley & sons, Inc.